

# PESO TEÓRICO DE LÁMINAS DE ACERO INOXIDABLE

ESPEORES			KILOGRAMOS POR HOJA				
CAL.	MM.	PULG.	KG / MT2	914 X 2438 3'X 8'	914 X 3048 3'X 10'	1219 X 3048 4'X 8'	1219 X 3048 4'X 10'
10	3.43	0.135	27.783	61.909	77.399	82.568	103.228
11	3.05	0.120	24.705	55.050	68.824	73.421	91.791
12	2.67	0.105	21.627	48.192	60.250	64.273	80.355
14	1.90	0.075	15.390	34.294	42.874	45.737	57.181
16	1.52	0.0595	12.312	27.435	34.299	36.590	45.745
18	1.22	0.048	9.882	22.020	27.529	29.368	36.716
20	0.89	0.035	7.209	16.064	20.083	21.424	26.785
22	0.74	0.0291	5.994	13.356	16.698	17.813	22.270
24	0.61	0.024	4.941	11.010	13.764	14.684	18.358
26	0.455	0.018	3.685	8.212	10.267	10.953	13.693
28	0.385	0.015	3.118	6.949	8.687	9.267	11.586
30	0.255	0.010	2.065	4.602	5.754	6.138	7.674

TABLAS DE PESOS - LÁMINA